

**Customer:** MMC Std profiles

**Product:** Altos Briquettes

**Customer Code:** MMC006

**Grade:** Altos Briquettes Mn/Al 75/25

**Agent:** None

**Grade ID:** 51

**Specifications**

**Physical Tests**

Element	Max	Min	Tolerance	Typical	
* Mn	76.0	74.0	0.04	75.0	%
* Si	0.100	-	0.004	0.030	%
* Fe	0.200	-	0.004	0.100	%
* Cu	0.100	-	0.004	0.010	%
* Mg	0.100	-	0.004	0.010	%
* Cr	0.100	-	0.004	0.003	%
* Zn	0.100	-	0.004	0.0050	%
* Ti	0.100	-	0.004	0.002	%
# Al	26.0	24.0	0.04	24.9	%

Test	Max Value
Tumble	0.00
Dissolution	0.00
Fines	3.00

\* Analysis per consignment.

# Al by Balance

**Packing:**

Spiral wrapped pallets each 100 x 10kg bags

**Instructions:**

**Special Req:**

**This product is manufactured using a selenium free process.**

**Electronic approval of this specification has been obtained from the Chief Chemist, Production Superintendent(s) and Marketing Manager. A hardcopy of this specification is kept in the Marketing files.**