

**Customer:** MMC Std profiles

**Product:** Salumba Briquettes

**Customer Code:** MMC006

**Grade:** Manganese Aluminium BQs 85/15

**Agent:** None

**Grade ID:** 58

**Specifications**

**Physical Tests**

Element	Max	Min	Tolerance	Typical	
* Mn	86.5	83.5	0	85.0	%
* Si	0.200	-	0.004	0.020	%
* Fe	0.300	-	0.004	0.010	%
* Cu	0.100	-	0.04	0.004	%
* Mg	0.100	-	0.04	0.010	%
* Cr	0.100	-	0.04	0.010	%
* Zn	0.100	-	0.04	0.0010	%
* Ti	0.100	-	0.04	0.001	%
# Al	16.5	13.5	0	15.0	%

Test	Max Value
Tumble	0.00
Dissolution	0.00
Fines	3.00

\* Analysis per consignment.

# Al by Balance

**Packing:**

1t boxes each 100 x 10kg bags with liners

**Instructions:**

Various packaging options are available:

25lb, 20lb, 10kg, in boxes or shrinkwrapped to pallets.

We are able to customise packaging configuration based on customer needs.

**Special Req:**

***This product is manufactured using a selenium free process.***

**Electronic approval of this specification has been obtained from the Chief Chemist, Production Superintendent(s) and Marketing Manager. A hardcopy of this specification is kept in the Marketing files.**